



Type	Grammage GSM (gm/m ²)	Bursting Factor (BF)	Cobb Value (g/m ²)		Moisture (%)	RCT (Kn/m)	
			Top	Bottom		MD	CD
Medium/Fluting Medium 18	140	18	40-50	40-50	6.5-7.5	1	0.8
Medium/Fluting Medium 18	175	18	40-50	40-50	6.5-7.5	1.6	1.3
Medium/Fluting Medium 18	200	18	40-50	40-50	6.5-7.5	1.8	1
Medium/Fluting Medium 18	225	17	40-50	40-50	6.5-7.5	2.4	2
Medium/Fluting Medium 18	250	16	40-50	40-50	6.5-7.5	2.7	2.2
Medium/Fluting Medium 20	140	20	40-50	40-50	6.5-7.5	1.1	0.9
Medium/Fluting Medium 20	175	20	40-50	40-50	6.5-7.5	1.7	1.4
Medium/Fluting Medium 20	200	20	40-50	40-50	6.5-7.5	1.9	1.6
Medium/Fluting Medium 20	225	19	40-50	40-50	6.5-7.5	2.6	2.1
Medium/Fluting Medium 20	250	18	40-50	40-50	6.5-7.5	2.8	2.3
Liner/Test Liner 22	140	22	30-40	40-50	6.5-7.5	1.5	1.2
Liner/Test Liner 22	175	22	30-40	40-50	6.5-7.5	2	1.7
Liner/Test Liner 22	200	22	30-40	40-50	6.5-7.5	2.4	2
Liner/Test Liner 22	225	22	30-40	40-50	6.5-7.5	2.9	2.4
Liner/Test Liner 22	250	21	30-40	40-50	6.5-7.5	3.2	2.6
Liner/Test Liner 22	275	20	30-40	40-50	7.5-8.5	3.8	3.1
Liner/Test Liner 25	140	25	30-40	40-50	6.5-7.5	1.6	1.3
Liner/Test Liner 25	175	25	30-40	40-50	6.5-7.5	2.2	1.8
Liner/Test Liner 25	200	25	30-40	40-50	6.5-7.5	2.6	2.1
Liner/Test Liner 25	225	25	30-40	40-50	6.5-7.5	3	2.5
Liner/Test Liner 25	250	24	30-40	40-50	6.5-7.5	3.3	2.7
Liner/Test Liner 25	275	23	30-40	40-50	7.5-8.5	4	3.2
Liner/Test Liner 25	300	22	30-40	40-50	7.5-8.5	4.3	3.5
Liner/Test Liner 28	140	28	30-40	40-50	6.5-7.5	1.7	1.4
Liner/Test Liner 28	175	28	30-40	40-50	6.5-7.5	2.3	1.9
Liner/Test Liner 28	200	28	30-40	40-50	6.5-7.5	2.7	2.2
Liner/Test Liner 28	225	28	30-40	40-50	6.5-7.5	3.2	2.6
Liner/Test Liner 28	250	27	30-40	40-50	6.5-7.5	3.5	2.8
Liner/Test Liner 28	275	26	30-40	40-50	7.5-8.5	4.2	3.4
Liner/Test Liner 28	300	24	30-40	40-50	7.5-8.5	4.6	3.7
Liner/Test Liner 28	400	21	30-40	40-50	8.0-9.0	5	4.1
Liner/Test Liner 32	140	32	30-40	40-50	6.5-7.5	1.8	1.45
Liner/Test Liner 32	175	32	30-40	40-50	6.5-7.5	2.4	1.95
Liner/Test Liner 32	200	32	30-40	40-50	6.5-7.5	2.8	2.3
Liner/Test Liner 32	225	31	30-40	40-50	6.5-7.5	3	2.7
Liner/Test Liner 32	250	30	30-40	40-50	6.5-7.5	3.8	3.1
Liner/Test Liner 35	140	35	30-40	40-50	6.5-7.5	1.9	1.5
Liner/Test Liner 35	175	35	30-40	40-50	6.5-7.5	2.5	2
Liner/Test Liner 35	200	35	30-40	40-50	6.5-7.5	2.9	2.4
Liner/Test Liner 35	225	33	30-40	40-50	6.5-7.5	3.7	2.9
Liner/Test Liner 35	250	32	30-40	40-50	6.5-7.5	4	3.3
Liner/Test Liner 35	275	30	30-40	40-50	7.5-8.5	4.4	3.6
Liner/Test Liner 35	300	38	30-40	40-50	7.5-8.5	4.9	4

Notes:-

Basis Weight Target: +-5%, RCT Target: +-10%

- RCT Test Value tested with L & W tester only
- Per TAPPI Standard conditions at 50+- 2% Relative Humidity, 23+-1°C temperature.
- Result per reel average in standard condition, except for basis weight & Moisture.
- This TDS supersedes all previous versions including undated ones.